

Technical data sheet

Aquasit cold casting compound, mixing bag

Item number: 2363036



Two-component casting compound Aquasit in an aluminium bag, for filling junction boxes in outdoor areas exposed to high levels of and long-lasting dampness. Also applicable for use against mechanical shock.

Processing time of 20 minutes after opening and mixing. Can be stored unopened at 0 to 40 °C up to 24 months from date of production. Practical experience, tests and approvals only apply in conjunction with OBO junction boxes.

Protection rating with appropriate junction box: IP68

Rated voltage: 400 V

Penetration resistance: >25 kV/mm to VDE 0291 Part 2

Operating temperature: -40 to +80 °C

Processing temperature: 5 to +40 °C

Halogen-free, silicon-free, isocyanate-free

Environmentally friendly and without the need to be labelled



Master data

Item number	2363036
Type	KVMM 1600
Description 1	Aquasit
Description 2	cast.compound for junct. boxes
Manufacturer	OBO
Dimension	1600 ml
Smallest sales unit	1
Unit of quantity	Piece
Weight	150 kg
Weight unit	kg/100 pc.

Dimensions

Length	330 mm
Width	210 mm
Height	52 mm

Technical data sheet

Aquasit cold casting compound, mixing bag

Item number: 2363036



Technical data

For Ex zone	Without
For Ex zone gas	Without
For Ex zone dust	Without
Contents	1600 g
Contents	1600 ml
Storage options in months	24
Material cable resin	Two-component polyurethane resin